

IN THE CLAIMS

Cancel claims 4 and 6 without prejudice or disclaimer.

5/11/11
C1

1. (Twice Amended) A multilayer film comprising a base material, a polymer resin layer and a metal deposited layer and/or a metal oxide deposited layer provided on the base material, wherein said polymer resin layer comprises a polymer produced by polymerization of an unsaturated compound having (a) two or more ethylenic bonds and/or (b) two or more acetylenic bonds in one molecule and having neither an acrylic group nor a methacrylic group, said polymer being present in said polymer resin layer in an amount of 80 % by weight or more based on said polymer resin layer,

wherein the thickness of said polymer resin layer is not less than 0.02 μm and not more than 1 μm , and

wherein said unsaturated compound is one or more compounds selected from the group consisting of an unsaturated fatty acid, an unsaturated fatty ester, and a terpene having an unsaturated bond.

B 1

2. (Twice Amended) A multilayer film according to claim 1, wherein the polymer resin layer is provided on the base material and the metal deposited layer and/or the metal oxide deposited layer is provided on the polymer resin layer.

3. (Twice Amended) A multilayer film according to claim 1, wherein the metal deposited layer and/or the metal oxide deposited layer is provided on the base material and the polymer resin layer is provided on the metal deposited layer and/or the metal oxide deposited layer.

506
C1
B2

10. (Twice Amended) A multilayer film according to claim 6, wherein the unsaturated fatty acid, unsaturated fatty ester, and terpene having an unsaturated bond are one or more compounds selected from the group consisting of coconut oil, soybean oil, linseed oil, palm kernel oil, safflower oil, china wood oil, tall oil, linolic acid, linolenic acid, ricinoleic acid, eleostearic acid, triglyceride linoleate, triglyceride linolenate, citral, citronellal, citronellol, nerolidol, geraniol, miltlen, linalool, and limonene.

506
C1
B3

22. (Amended) A multilayer film comprising a base material, a polymer resin layer and a metal layer and/or a metal oxide layer provided on the base material, wherein said polymer resin layer comprises a polymer produced by polymerization of an unsaturated compound having (a) two or more ethylenic bonds and/or (b) two or more acetylenic bonds in one molecule and having neither an acrylic group nor a methacrylic group, said polymer being present in said polymer resin layer in an amount of 80 % by weight or more based on said polymer resin layer, wherein the thickness of said polymer resin layer is not less than 0.02 μm and not more than 1 μm , and wherein said unsaturated compound is one or more compounds selected from the group consisting of an unsaturated fatty acid, an unsaturated fatty ester, and a terpene having an unsaturated bond.